

PLEXIGLAS® Hi-Gloss NTA-1

Product Profile:

PLEXIGLAS® Hi-Gloss NTA-1 is an impact-modified compound with a high heat deflection temperature based on polymethyl methacrylate (PMMA).

Besides the well-known properties of PLEXIGLAS® molding compound, such as

- good flow
- high mar resistance
- good weather resistance
- good polishability,

PLEXIGLAS® Hi-Gloss NTA-1 offers the added benefits of

- increased impact strength
- good heat deflection temperature under load.

Application:

PLEXIGLAS® Hi-Gloss NTA-1 is particularly suitable for injection molding technical components.

Owing to its superior brilliance, high-gloss (Class A) surfaces can be obtained in opaque colors.

Examples:

add-on automotive body parts, mirror housings, pillar panels, spoilers

Processing:

PLEXIGLAS® Hi-Gloss NTA-1 can be processed on machines with 3-zone general purpose screws for engineering thermoplastics.

Physical Form / Packaging:

PLEXIGLAS® Hi-Gloss NTA-1 compounds are supplied as pellets of uniform size, packaged in 25kg polyethylene bags or in 500kg boxes with PE lining; other packaging on request.

Properties:

	Parameter	Unit	Standard	PLEXIGLAS® Hi-Gloss NTA-1
Mechanical Properties				
Tensile Modulus	1 mm/min	MPa	ISO 527	2700
Yield Stress	50 mm/min	MPa	ISO 527	68
Yield Strain	50 mm/min	%	ISO 527	5
Nominal Strain @ Break		%	ISO 527	10
Charpy Impact Strength	23°C	kJ/m ²	ISO 179/1eU	33
Thermal Properties				
Vicat Softening Temperature	B / 50	°C	ISO 306	110
Glass Transition Temperature		°C	IEC 10006	120
Temp. of Deflection under Load	0.45 MPa	°C	ISO 75	103
Temp. of Deflection under Load	1.8 MPa	°C	ISO 75	102
Fire Rating			DIN 4102	B2
Glow Wire Ignition Temperature		°C	IEC 60695-2	675
Rheological Properties				
Melt Volume Rate, MVR	230°C / 3.8kg	cm ³ /10min	ISO 1133	3
Other Properties				
Density		g/cm ³	ISO 1183	1.18
Water Absorption in Water		%	ISO 62	> 3
Recommended Processing Conditions				
Predrying Temperature		°C		max. 100
Predrying Time in Desiccant-Type Drier		h		2 - 3
Melt Temperature		°C		220 - 250
Mold Temperature (Injection Molding)		°C		50 - 85

All listed technical data are typical values intended for your guidance. They are given without obligation and do not constitute a materials specification.

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

The Business Unit Performance Polymers of Evonik is a worldwide manufacturer of PMMA molding compounds sold under the PLEXIGLAS® trademark on the European, Asian, African and Australian Continent and under the trademark ACRYLITE® in the Americas.

® = registered trademark

PLEXIGLAS and PLEXIMID are registered trademarks of Evonik Röhm GmbH, Darmstadt, Germany

Evonik Röhm GmbH Kirschenallee 64293 Darmstadt
 Telefon +49 6151 18-4711 Telefax +49 6151 18-3177
www.plexiglas-polymers.com

Ref. No.: MC85-E v0160 Date: 2011-04-04